



Note :
Due to keeping innovation,
the specification and
Machine pictures or color
are subject to alteration
without notice!

Anti-yellowing & Aging Tester

This product can do two tastes: again and anti-yellowing.

Aging:

The machine can promote the deterioration of sulfur rubber to calculate the tensile and elongation changing rate after and before heating. It is generally acknowledged that doing the test at 70°C for one day is theoretically equal to exposing to the ambient air for 6 months.

Anti-yellowing:

The machine simulates the ambient environment to exposing to the ultraviolet radiation, the appearance change is generally acknowledged that doing the test at 50°C for nine hours is theoretically equal to exposing to the ambient air for 6 months.

Inner Dimension (D x W x H) (mm)	500 x 500 x 600
Temperature Range	Room temperature ~ 200°C
Control Mode	Automatic calculation controller 0.1°C
Temperature Display	1°C
Distribution Precision	± 1°C (at - 100°C)
Time Memory	0-999 hours, power failure memory type, with buzzer
Wheel Speed	φ 45cm, 10 ± 2 round / min
UV Light Source	UV 300w bulb
Standard Accessories	2pcs Shelf board
Heating Method	Hot air circulation
Security Protection	Over temperature power-off indicator light, safety overload switch ammeter
Manufacturing Material	Internal: SUS#304 stainless steel; External: high-level paint SUS#304 stainless steel
Outside Dimension	114Lx94Wx130Hcm
Weight	140kg
Power	1 φ, AC220V/50HZ, 15A(can be customized)